



Physical Property	Typical Value	Test Method
Ductility @ 77 °F, 5cm/min	5.0 min	-
Flash Point	>390 °F	-
Softening Point	320 °F	-
Specific Gravity @ 77 °F	1.20 - 1.35	-

Description

Rubr-Nek[®] LTM is a butyl rubber base flexible gasket-type sealant for utility vaults, sewer manholes, waste water structures, storm sewer pipe and culverts, wet wells, etc. It stays flexible and is easily applied in temperatures as low as 30 °F. **Rubr-Nek[®] LTM**'s formulation of 100% solids with top-quality partially vulcanized butyl rubber provides exceptional shape retention, in combination with outstanding adhesion and cohesion. The material does not shrink, harden or oxidize, and retains compressibility throughout a wide range of deflections occurring over periods of time.

Application

Clean: Joint surfaces should be clean and dry. For maximum bond strength on horizontal pipe installations, use **Rubr-Nek[®] Primer** before installing **Rubr-Nek[®] LTM**. (On vertical installations, the primer is not normally required).

Prep: Trench conditions shall be such that pipe jointing can be accomplished without getting mud, silt, gravel or other foreign matter into the joint. In general, this means that the trench should be adequately dewatered with a firm bottom free of muck.

Rubr-Nek[®] LTM is quickly installed and no special tools are needed. It bonds instantly to joint surfaces and to itself, and is quickly formed into a continuous seal around the circumference or perimeter of the joint area.

A **Rubr-Nek[®] LTM** coil of proper size is removed from the carton and positioned on the joint and pressed in place. If necessary, a second coil is butted end-to-end against the first, and the procedure continued around the circumference or perimeter of the joint area. All protective paper wrappers can be left in place until just before coupling the joint in the ditch.

Placement on the Joint: Dimensions and configurations of the precast concrete joint, and the tightness of the joint when "homed" determine the volume of sealant needed, and its position on the joint.

Backfilling: Backfilling can begin as soon as jointing has been completed.

Handling: Pipe handling after **Rubr-Nek[®] LTM** has been affixed shall be carefully controlled to avoid bumping the gasket and thus displacing it, or covering it with dirt or other foreign material. Any gasket so disturbed shall be removed and replaced.

Pipe Alignment: Care shall be taken to properly align the pipe before joints are forced home. During insertion of the tongue – in the case of tongue and groove pipe – the pipe shall be partially supported to maintain concentricity until the plastic gasket is properly compressed in the joint space.

Pull-up or Push-up Pressure: Sufficient pressure shall be applied in making the joint to assure that the joint is properly jointed.

Packaging

12 (1/2in x 21.75ft) Coils/Case, 8 (.75in x18ft) Coils/Case, 6 (1in x 14.5ft) Coils/Case
4 (1.5in x10.5ft) Coils/Case, 5 (1.25in x14.5ft) Coils/Case, 4 (2in x 7.5ft) Coils/Case

For more information, visit www.henry.com or for technical assistance call us at 800-486-1278. For more information on Henry's[®] product warranty and liability disclaimer please visit www.henry.com/warranty. Refer to the Safety Data Sheet prior to using this product. The Safety Data Sheet is available at www.henry.com or by emailing Henry[®] Product Support at productsupport@henry.com or by calling 800-486-1278.

Henry[®] is a registered trademark of Henry Company

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry[®] Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.